Product Change Notification

Date Issued :	October 06, 2026	**PCN Number :**	518883
Reason for Change :	Change Supplier		
Description of Change :	Resin PN 1302190096 has changed, and its color is no longer transparent but natural. As a result, it can no longer be used for the same purpose as before. For this reason, we propose using the same resin currently used at the Poland plant, PN 0899920918.		
Reason for Short Notice :	Special Request		
Assessment of Change :	No change to parts - Form/Fit/Function		
Planned Implementation Date :	February 19, 2027		
Customer Sample Availability Date:	November 13, 2026		

Last date to request Samples by Customer : November 02, 2026

Please note if Samples are not requested as per Customer Samples Request date, it may take additional 4-6 weeks to arrange Samples.

Traceability Code Markings / Date : No special marking on the product or packaging

BEFORE

Part Number	Description
1302190096	ESTANE (PUR) NATURAL

AFTER

Part Number	Description
899920918	TPU NATURAL UL94HB

1 1

Molex Confidential Information
© 2016 Molex – All Rights Reserved. Unauthorized Reproduction/Distribution is Prohibited.

Overview

- Resin PN 1302190096 has changed color from transparent to natural. Therefore, it already meets the required characteristics.For this reason, we propose using resin PN 0899920918, which is transparent.
-
- Product Impact
  - "No impact to fit, form or function"
- Part Number Impact
  - See attached list
- PCN will be implemented once all required qualification / validation has been completed, and all necessary approvals have been obtained

Molex Confidential Information
© 2016 Molex – All Rights Reserved. Unauthorized Reproduction/Distribution is Prohibited.

molex

1302190096

Lubrizol ESTANE® ZHF 90AT8H NAT 02

Technical Data Sheet

Type: ESTANE® ZHF 90AT8H NAT 02 is a non-halogen, flame retardant, aromatic polyether-based thermoplastic polyurethane.

Application: Extrusion

Physical Properties	Value (Metric)	Unit	Test Method
Hardness	A/1: 87	Shore A	ISO 868
Specific Gravity	1.21	g/cm³	ISO 1183
Tensile Strength	28	MPa	ISO 527-200
Ultimate Elongation	500	%	ISO 527-200
Tensile Stress at:			
- 100 % Elongation	7	MPa	ISO 527-200
- 300 % Elongation	10	MPa	ISO 527-200
Abrasion Loss	36	mm³	ISO 4649-A
Tear Strength nicked	53	kN/m	ISO 34-1B

• Based on extruded strips
• Prior to testing samples were conditioned at 23°C for 48 hours
• Listed values are "typical (average) values" and should/cannot be applied for specification purposes.

Application Specific Properties	Value (Metric)	Unit	Test Method
UL Flame Rating	V0-0.8 mm	-	UL-94
LOI	25	%	ASTM D-2863
UL Temperature rating	105	°C	UL-1581
Smoke Density (0.75 mm)	TBD	Flaming DM Non flaming DM	ASTM E662

Material Preparation

• Prior to processing, **ESTANE® ZHF 90AT8H NAT 02** must be dried at 100°C for 4 hours.
• It is recommended to dry the material in a vacuum or dehumidifying type dryer. Target dew point should be -40°C.
• Depending on the applied processing technique, the maximum moisture level should be 0.02%.

Molex Confidential Information
© 2016 Molex – All Rights Reserved. Unauthorized Reproduction/Distribution is Prohibited.

molex

0899920918

General Productinformation
Elastollan® 11 95 A 10
Elastollan® BMB 11 95 A 10

® = registered trademark of BASF Polyurethanes GmbH

BASF
We create chemistry

Characteristic:
Thermoplastic Polyether-Polyurethane with outstanding hydrolysis resistance, low temperature flexibility and high resistance to micro-organisms.

The product can also be offered as BMBcert™. Due to the Massbalance approach the product properties do not change.

Property	Unit	Value	Test method according to
Hardness	Shore A	96	DIN ISO 48-4 (3s)
Hardness	Shore D	48	DIN ISO 48-4 (3s)
Density	g/cm³	1,15	DIN EN ISO 1183-1-A
Tensile strength	MPa	55	DIN 53504-S2
Elongation at break	%	500	DIN 53504-S2
Stress at 20% elongation	MPa	6	DIN 53504-S2
Stress at 100% elongation	MPa	10	DIN 53504-S2
Stress at 300% elongation	MPa	18	DIN 53504-S2
Tear strength	kN/m	100	DIN ISO 34-1Bb
Abrasion loss	mm³	35	DIN ISO 4649-A
Compression set 23°C / 72 hours	%	30	DIN ISO 815-1
Compression set 70°C / 24 hours	%	45	DIN ISO 815-1
Tensile strength after storage in water at 80°C for 42 days	MPa	37	DIN 53504-S2
Elongation at break after storange in water at 80°C for 42 days	%	500	DIN 53504-S2
Notched impact strength (Charpy) at +23°C	kJ/m²	no break	DIN EN ISO 179-1
Notched impact strength (Charpy) at -30°C	kJ/m²	no break	DIN EN ISO 179-1
Burning behaviour		HB	UL 94

The plaques are manufactured by injection moulding from pre-dried granules (water content less 0,02%). Test plaques are aged 20 hrs at 100°C. Specimens are cut from 2 or 6 mm test plaques. The test conditions: 23°C ± 2°C and 50% ± 6% rel. humidity.

Molex Confidential Information
© 2016 Molex – All Rights Reserved. Unauthorized Reproduction/Distribution is Prohibited.

4

molex

PCN Qualification and Validation Plan

- Below is the List of Part Numbers will be used for internal qualification & validation purposes.
- Samples and Qualification data will be provided upon request.

1200670066 1200870658

You may address inquires regarding this PCN by clicking on the below link
mailto:pcn_coordinator@molex.com?subject=PCN_Notification:518883
or contact your Local Sales Engineer.

Note: While responding, please retain " **PCN Notification: 518883** " in the e-mail Subject line for faster response.

Molex, LLC
2222 Wellington Court
Lisle, IL 60532
TEL (800) 786-6539
www.molex.com

PCN No	Part List
518883	848569110
518883	848569111
518883	1200390001
518883	1200650106
518883	1200650565
518883	1200651027
518883	1200651028
518883	1200660067
518883	1200660071
518883	1200660106
518883	1200660138
518883	1200661765
518883	1200661873
518883	1200670020
518883	1200670024
518883	1200670029
518883	1200670033
518883	1200670050
518883	1200670056
518883	1200670065
518883	1200670066
518883	1200670069
518883	1200670078
518883	1200670080
518883	1200670088
518883	1200670089
518883	1200670090
518883	1200670091
518883	1200670102
518883	1200670108
518883	1200670111
518883	1200670150
518883	1200670151
518883	1200670166
518883	1200670167
518883	1200670178
518883	1200670182
518883	1200670183
518883	1200670185
518883	1200670188
518883	1200670189
518883	1200670195
518883	1200670196
518883	1200670199
518883	1200670203

518883 1200670213
518883 1200670214
518883 1200670220
518883 1200670221
518883 1200670222
518883 1200670223
518883 1200670224
518883 1200670227
518883 1200670229
518883 1200670231
518883 1200670233
518883 1200670234
518883 1200670235
518883 1200670242
518883 1200670243
518883 1200670244
518883 1200670245
518883 1200670246
518883 1200670247
518883 1200670248
518883 1200670256
518883 1200670257
518883 1200670259
518883 1200670261
518883 1200670283
518883 1200670296
518883 1200670297
518883 1200670300
518883 1200670302
518883 1200670308
518883 1200670309
518883 1200670313
518883 1200670314
518883 1200670315
518883 1200675003
518883 1200675004
518883 1200675005
518883 1200860419
518883 1200860420
518883 1200860421
518883 1200860422
518883 1200860423
518883 1200860424
518883 1200860463
518883 1200860526
518883 1200870219

518883 1200870658
518883 1200880098
518883 1200880099
518883 1200880100
518883 1200880101
518883 1300060716
518883 1300160321
518883 1300280264
518883 1300280266
518883 1300280267
518883 1300280270
518883 1300280271
518883 1300280274
518883 1300280275
518883 1300300079
518883 1300390072
518883 1300390371